

*Technical Data Sheet Final version ; edition 2 Date: 23/10/02* 

## DYMO LabelWriter Removable

## (1) Description

DYMO LabelWriter Removable product is a paper label with a removable adhesive. The product is supplied on a roll. The labels are printed on the LabelWriter with a thermo-direct printing process, which involves no messy ink ribbons, toner or cartridges. Individual labels or whole rolls can be printed with laser like print quality. The product is recommended for indoor use only. Direct and indirect exposure to sunlight as well as high temperatures and high humidity must be avoided.

Property		Unit	Value	Test method
1.	General			
-	Thickness tape Thickness liner	Micron Micron	155 ± 10 55 ± 5	Micrometer
-		WICTON	35 ± 5	
2.	Adhesive properties		Dwell <sup>1</sup>	
	to stainless steel to glass to PVC to textured ABS to powder coated steel to wood to polypropylene film matt to polypropylene film glossy to polyethylene to Lever Arch File to steel computer casing	N/25mm	20 min 24 hrs   3 4   3 4   2 3   2 3   1 3   1 2   3 4   3 4   3 4   1 2   3 4   3 4   1 1   1 1	PSTC-1

<sup>&</sup>lt;sup>1</sup> Dwell denotes the contact time between label and surface

2	Abreeien registeres <sup>2</sup> of text			
3.	Abrasion resistance <sup>2</sup> of text Printed in LabelWriter Turbo 330			
-	Pencil erasure	30x	No visible effect	Crockmeter,
-	Polystyrene pin Sandpaper	30x 30x	No visible effect No visible effect	900g woight/arm
-	Запарары	30%		weight/arm
4.	Light stability of printed label <sup>3</sup>			
_	in sun tester with glass filter		Background yellows.	
	(corresponds with direct exposure		Text fades but still	
	behind 3 mm window glass)		legible.	
5.	Temperature stability			
-	Application temperature	°C	Room temperature	
-	Service temperature		-20 to 50 °C	
	30 days in consumer deep freezer		No visible effect	
	24h at 50°C		No visible effect	
	10 minutes at 85°C		No changes in print	
			quality. Background becomes grey.	
6.	Humidity resistance of applied label		giey.	
-	30 days at 40°C, 95 % R.H. (on alu panel)		To be done	
7.	Shelf life of label roll			
_	1 year at 5-25°C and 40-80%		Avoid exposure to	
	relative humidity in its original		heat, humidity &	
	packaging		sunlight	

<sup>&</sup>lt;sup>2</sup> Abrasion resistance: The printed labels are subjected to different scratching sources for a fixed number of cycles with a finger weight of 900g. <sup>3</sup> Resistance up to wool scale 4. This corresponds with 24 summer days and 48 winter days exposure behind window

glass.