

## FABRIANO 2 L [110 g/m<sup>2</sup>]

Carta a superficie naturale, fabbricata con il 100% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste. FSC MIXED CoC 000010

Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706.

La carta da disegno più qualificata in Italia per i ragazzi delle scuole elementari e medie. Indicata per matita, pastello, cera, pennarello, china. La filigrana riproduce il marchio ed il logotipo FABRIANO ed il numero 2,

Uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC MIX CoC 000010

The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706.

The most qualified paper for school beginners and intermediate students. Is suitable for pencils, pastels, wax crayon and indian inks. The watermark reproduces brand and logotype Fabriano and number 2.

CARATTERISTICHE - PROPERTIES	METODOLOGIA - METHOD	U.M.	TARGET	Min.	Max.
Grammatura Grammage	UNI EN ISO 536 I.O. 10 P44 004	g/m <sup>2</sup>	110,0	105,0	115,0
Spessore Thickness	UNI EN 20534 I.O. 10 P44 005	microns		125,0	145,0
Assorbimento acqua [Cobb] Water absorptiveness [Cobb]	UNI EN 20535 I.O. 10 P44 010	g/m <sup>2</sup>			32,0
Grado di Bianco Brightness	UNI 7623 I.O. 10 P44 006	%	98,0	96,5	99,5
Ruvidità [Bendtsen] Roughness [Bendtsen]	UNI 7626-2 I.O. 10 P44 007	ml/1'		120,0	260,0
Res. Strappo superficiale Wax pick test [Dennison]	UNI 9073 I.O. 10 P44 018	n°		14,0	