

VINILCHIMICA

**TYPE OF MATERIAL
SUPER/ATO**

rigid PVC based compound

STABILIZATION

calcium zinc

APPLICATION

rigid extrusion for external use

| TECHNICAL PROPERTIES | UNITS | VALUES | TEST METHODS |
|----------------------------------|-------------------|---------------|---------------------|
| Specific gravity | g/cm ³ | 1,51 | ASTM D 792 |
| VICAT 5Kg. | °C | 80 | ISO 306 |
| ULTIMATE YIELD STRESS | MPa | 42 | ISO 527 |
| ULTIMATE TENSILE STRESS | MPa | 39.5 | ISO 527 |
| ULTIMATE ENLONGATION AT BREAK | % | 105 | ISO 527 |

In answer to the demands of the market, VINILCHIMICA follows a policy of research and development that aims at the manufacturing of better and better quality products.

Every information contained in this document is given in good faith but without assurance or guarantee of any type, implicit or expressed.

The indicated specific gravity here expressed refers to the mixed compound lacking in pigments. The pigment added can carry to variations, in increase, of the specific gravity until 0.06 g/cm³.


Please, do not hesitate to contact VINILCHIMICA for every information concerning the quality of the different types, or, if it were necessary, for assistance in the solution of a particular problem.

Last revision date , 18/02/13

Printing date, 23/02/15

For further information please do contact:

VINILCHIMICA S.R.L. Via Sonna, 6 24030 CAPRINO BERGAMASCO(BG) Tel. 035781123 Fax
035783609 e-mail info@vinilchimica.it



VINILCHIMICA

**TYPE OF MATERIAL
SUPER/L T2 CZ**

rigid PVC based compound

STABILIZATION

calcium zinc

APPLICATION

rigid extrusion for external use

| TECHNICAL PROPERTIES | UNITS | VALUES | TEST METHODS |
|----------------------------------|-------------------|---------------|---------------------|
| Specific gravity | g/cm ³ | 1,51 | ASTM D 792 |
| VICAT 5Kg. | °C | 80 | ISO 306 |
| ULTIMATE YIELD STRESS | MPa | 42 | ISO 527 |
| ULTIMATE TENSILE STRESS | MPa | 39.5 | ISO 527 |
| ULTIMATE ENLONGATION AT BREAK | % | 105 | ISO 527 |

In answer to the demands of the market, VINILCHIMICA follows a policy of research and development that aims at the manufacturing of better and better quality products.

Every information contained in this document is given in good faith but without assurance or guarantee of any type, implicit or expressed.

The indicated specific gravity here expressed refers to the mixed compound lacking in pigments. The pigment added can carry to variations, in increase, of the specific gravity until 0.06 g/cm³.

Please, do not hesitate to contact VINILCHIMICA for every information concerning the quality of the different types, or, if it were necessary, for assistance in the solution of a particular problem.

Last revision date , 17/10/11

Printing date, 05/06/15

For further information please do contact:

VINILCHIMICA S.R.L. Via Sonna, 6 24030 CAPRINO BERGAMASCO(BG) Tel. 035781123 Fax
035783609 e-mail info@vinilchimica.it