

DESCRIZIONE DESCRIPTION

Carta a superficie monoruvida, fabbricata con il 100% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste. FSC MIXED CoC 000010. Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706. Si presta a molteplici utilizzazioni quali: disegno, cartellonistica, schizzi, collages, copertine, depliant, inserti, cartelline, biglietti augurali, inviti, menù, etc. Disponibile in una gamma di colori molto ampia.

Monotexture uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC MIX CoC 000010. The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706. Suitable for drawing, posters, sketches, collage, covers, leaflets, folders, menus, greeting cards, announcements, etc. Available in a wide gamut of colours.

CONNOTAZIONI FEATURES



DATI TECNICI TECHNICAL DATA

| CARATTERISTICHE PROPERTIES | METODOLOGIA METHOD | TARGET | MIN. | MAX. |
|---|-----------------------|--------|------|------|
| Grammatura Grammage (g/m ²) | ISO 536 | 220 | 210 | 230 |
| Spessore Thickness (microns) | ISO 534 | 320 | 300 | 340 |
| Assorbimento acqua Water absorptiveness (Cobb - g/m ²) | ISO 535 | 26 | | 32 |
| Grado di bianco Brightness (%) | ISO 2470 | 107,5 | 106 | 109 |
| Ruvidità (Bendtsen) TS Roughness (Bendtsen) TS (ml/1') | ISO 8791/2 | 2500 | 2000 | 3000 |
| Ruvidità (Bendtsen) WS Roughness (Bendtsen) WS (ml/1') | ISO 8791/2 | 800 | 500 | 1100 |