

COPY LUCE [75 g/m²]

Carta a superficie naturale, fabbricata con il 100% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste. FSC MIX CQ CoC 000010
 Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706.
 Alto grado di bianco. Qualità ottima. Altissime prestazioni per copie di prestigio. Idonea per fotocopie, stampa laser, ink-jet e fax a carta naturale.

Uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC MIX CQ CoC 000010
 The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706.
 High grade of white. Optimum quality. High performance for perfect copies. Suitable for photocopying, laser printing, ink-jet and faxing.

CARATTERISTICHE - PROPERTIES	METODOLOGIA - METHOD	U.M.	TARGET	Min.	Max.
Umidità Assoluta Moisture Content	ISO 287 E.d.P.	%		4,2	4,8
Grammatura Gramaqe	UNI EN ISO 536 I.O. 10 F44 010	g/m ²	75,0	73,0	77,0
Spessore Thickness	ISO 534 I.O. 10 F44 013	microns	103,0	98,0	108,0
Assorbimento acqua [Cobb] Water absorptiveness [Cobb]	ISO 535 I.O. 10 F44 003	g/m ²			30,0
Grado di Bianco Brightness	ISO 2470 I.O. 10 F44 017	%	109,5	108,0	111,0
C.I.E. Whiteness C.I.E. Whiteness	ISO 11475 I.O. 10 F44 017		163,0	161,0	165,0
Opacità Opacity	ISO 2471 I.O. 10 F44 017	%		90,0	
Ruvidità [Bendtsen] Roughness [Bendtsen]	ISO 8791/2 I.O. 10 F44 011	ml/1'		250,0	350,0