



tesa® 64621 Industry

Product Information



Double-sided transparent self-adhesive tape

Product Features

- With the hotmelt adhesive, tesa® 64621 is solvent free and offers a very high tack.
- tesa® 64621 is protected by a siliconized paper liner.

tesa® 64621 is a transparent double-sided self-adhesive tape consisting of a PP-carrier and a synthetic rubber adhesive mass system (hotmelt).

Application Fields

- General purpose fixing tape
- Self-adhesive mounting of decorative and packaging materials
- Bonding of foils, fabrics, paper and plastic materials

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|---------------------|----------------------|-------------|
| • Type of liner | glassine | • Color of liner | yellow |
| • Weight of liner | 78 g/m ² | • Total thickness | 90 µm |
| • Backing material | PP film | • Thickness of liner | 70 µm |
| • Type of adhesive | synthetic rubber | • Color | transparent |

Product Properties/Performance Values

- | | | | |
|------------------------------------|-------|-------------------------------------|-------|
| • Elongation at break | 140 % | • Temperature resistance short term | 80 °C |
| • Temperature resistance long term | 40 °C | | |

Adhesion to Values

- | | | | |
|----------------------|----------|-------------------------|----------|
| • Steel (initial) | 10 N/cm | • PVC (initial) | 9 N/cm |
| • PE (initial) | 5 N/cm | • PP (initial) | 8 N/cm |
| • PP (after 14 days) | 9 N/cm | • Steel (after 14 days) | 15 N/cm |
| • PE (after 14 days) | 6.5 N/cm | • PVC (after 14 days) | 9.5 N/cm |

Additional Information

Additional liner variants:
PV6 red MOPP-film, 80µm

For latest information on this product please visit
<http://l.tesa.com/?ip=64621>



tesa[®] 64621

Industry

Product Information

Additional Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit
<http://l.tesa.com/?ip=64621>