FABRIANO 4 R [200 g/m²]

Carta a superficie naturale, fabbricata con il 100% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste. FSC MIXED CoC 000010
Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706. L'alto grado di collatura e l'ottima resistenza alle gomme di qualsiasi durezza sono le prerogative principali della FABRIANO 4.
E' indicata per usi artistici (tempera, matita, acquerello), ma anche per stampe d'arte (serigrafia, litografia). Su ogni foglio è riportato in un angolo il marchio a secco del prodotto.

Uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC MIX CoC 000010
The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706. The good sizing and the excellent resistance of this paper to erasers are the principal characteristics of FABRIANO 4.
Is suitable for pencils, tempera and watercolour as well as for art prints (lithography and silkscreen). The trademark F4 is embossed in the corner of each sheet.

CARATTERISTICHE - PROPERTIES	METODOLOGIA - METHOD	U.M.	TARGET	Min.	Max.
Grammatura Grammage	UNI EN ISO 536 I.O. 10 P44 004	g/m²	200,0	192,0	208,0
Spessore Thickness	UNI EN 20534 I.O. 10 P44 005	microns		270,0	310,0
Assorbimento acqua [Cobb] Water absorptiveness [Cobb]	UNI EN 20535 I.O. 10 P44 010	g/m²			36,0
Grado di Bianco Brightness	UNI 7623 I.O. 10 P44 006	%	100,5	99,0	102,0
Res. Strappo superficiale Wax pick test [Dennison]	UNI 9073 I.O. 10 P44 018	n°		16,0	